

**HJC INTERNATIONAL CO.,LTD**

EMAIL:INFO@HJCGREEN.COM TEL:86-731-8223 5826,
 ADD:ROOM 317, 58 ZHONGCHUANG BUILDING, YUELU DISTRICT, CHANGSHA, HUNAN,
 CHINA, 410006
 WWW.HJCGREEN.COM

Much higher flow rate than other countertype in the market. Get more clean water!

Membrane Element		2G 2012-180
Performance	Permeate Flow:	180 GPD
	Salt Rejection:	95-96%
Type	Configuration:	Spiral Wound
	Membrane Polymer:	Composite Polyamide
	Membrane Active Area:	0.84m ²
Application Data*	Maximum Applied Pressure:	150psi (1.03MPa)
	Maximum Chlorine Concentration:	<0.1ppm
	Maximum Operating Temperature:	113°F (45°C)
	pH Range, Continuous (Cleaning):	2-11
	Maximum Feed Water TDS:	1,000ppm
	Maximum Feed Silt Density Index:	SDI 5

* The limitations shown here are for general use. For specific projects, operating at more conservative values may ensure the best performance and longest life of the membrane.

Test Conditions

The stated performance is initial (data taken after 30 minutes of operation), based on the following conditions:

200ppm NaCl Solution
 60psi (0.41MPa) Applied Pressure
 77 °F (25°C) Operating Temperature
 15% Permeate Recovery
 6.5-7.5 pH Range



A. Inch(mm)	B. Inch(mm)	C. Inch(mm)	D1. Inch(mm)	D2. Inch(mm)	E. Inch(mm)	Weight.lbs(kg)
11.73(298)	1.96(49)	0.67(17)	0.83(21)	0.83(21)	10.07(256)	0.55(0.25)